



MASTER ALLOYS



35% Aluminum – 65% Molybdenum Standard Product Analysis

Element	Specification
Aluminum	32-38%
Molybdenum	62-68%
Carbon	0.07% max.
Chromium	0.10% max.
Copper	0.10% max.
Iron	0.50% max.
Magnesium	0.10% max.
Manganese	0.10% max.
Nickel	0.10% max.
Nitrogen	0.03% max.
Oxygen	0.10% max.
Silicon	0.30% max.
Tungsten	0.04% max.

Other Product Compositions: On request.


Size: Minus U.S. No. 20 (850 µm);
Other Sizes Available on Request.

Inspection: 100% Inspected under Visible Light.

Packaging: Per Customer Request.

October 1, 2002

STRATCOR, Inc. • A Subsidiary of Strategic Minerals Corporation
4955 Steubenville Pike; Suite 305 • Pittsburgh, Pennsylvania 15205-9604 • U.S.A.
Tel: 412.787.4500 • 800.573.6052 • Fax: 412.787.5030 • E-mail: info@stratcor.com • www.stratcor.com

 is a registered trademark of Strategic Minerals Corporation.